

# FPM 75 / 80-01-75005

75 ShA / peroxide crosslinked / black

- Fluorinated rubber
- Tetrapolymer, Type F
- Very good temperature resistance, high chemical resistance.
- Excellent resistance to ozone, ageing and weathering.

Property	Value	Unit	DIN Standard
Hardness	75 ±5	Shore A	DIN ISO 7619-1
Density	1,91 ±0,03	g/cm <sup>3</sup>	DIN EN ISO 1183-1
Tensile strength at 100% elongation	6,2	N/mm <sup>2</sup>	DIN 53504
Elongation at break	255	%	DIN 53504
Tensile strength	20,4	N/mm <sup>2</sup>	DIN 53504
Compression set 175°C/24h	17,6	%	DIN ISO 815-1 B
Rebound resilience	7	%	DIN ISO 53512
Tear resistance	5,5	N/mm	DIN ISO 34-1 A
Abrasion	110	mm <sup>3</sup>	DIN ISO 4649 B
Embrittlement point	ca. -30	°C	ASTM D 2137
min. operating temperature	-20	°C	static
max. operating temperature	+210	°C	constantly

All above stated data result from random tests which were taken from the ongoing production. All data were established based on standard test-specimen according to ISO, DIN and ASTM standards and can basically not be carried over to the construction element.

Our applied technical advice, either oral, written or through tests is given according to our best knowledge. However, this information is to be considered as non-obligatory instruction, also in terms of any protective rights of a third party, and does not exempt you from testing our product in reference to its suitability for the intended process and purpose. Utilisation, application and processing of the products occur entirely outside of our control and are therefore exclusively your responsibility. However, should a case of liability come into question, it will be limited to all damages in the value of the product which we delivered and you used. By all means, we do warrant the impeccable quality of our products in accordance with our general sales and delivery conditions.