

# HPU gecco

Hydrolysis-resistant Polyurethane

Standard colour: green, similar to RAL 6016

- HPU for standard applications
- Resistant to mineral oils, HFD-U and HETG-fluids, sour oils and gases, cold water as well as diluted acids and bases
- Applicable for static seals, rod and piston seals, wiper seals and rotary seals

Properties	Value	Unit	DIN Standard
Hardness	94 ±3	Shore A	DIN ISO 7619-1
Hardness	49 ±3	Shore D	DIN ISO 7619-1
Density	1,194	g/cm <sup>3</sup>	DIN EN ISO 1183-1
100% Modulus	10,9	MPa	DIN 53504
300% Modulus	20,6	MPa	DIN 53504
Elongation at break	460	%	DIN 53504
Tensile strength	36,0	MPa	DIN 53504
Compression set 70°C/22h	23	%	DIN ISO 815-1
Compression set 70°C/70h	27	%	DIN ISO 815-1
Compression set 100°C/22h	40	%	DIN ISO 815-1
Rebound resilience	36	%	DIN ISO 4662:2017
Tear resistance	39,2	N/mm	DIN ISO 34-1 A
Abrasion resistance	26	mm <sup>3</sup>	DIN ISO 4649 B
min. Service temperature	-30	°C	
max. Service temperature	+110	°C	

All above stated data result from random tests which were taken from the ongoing production. All data were established based on standard test-specimen according to ISO, DIN and ASTM standards and can basically not be carried over to the construction element.

Our applied technical advice, either oral, written or through tests is given according to our best knowledge. However, this information is to be considered as non-obligatory instruction, also in terms of any protective rights of a third party, and does not exempt you from testing our product in reference to its suitability for the intended process and purpose. Utilisation, application and processing of the products occur entirely outside of our control and are therefore exclusively your responsibility. However, should a case of liability come into question, it will be limited to all damages in the value of the product which we delivered and you used. By all means, we do warrant the impeccable quality of our products in accordance with our general sales and delivery conditions